



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁷ : B01D 69/08, 71/38, 67/00	A1	(11) International Publication Number: WO 00/43115 (43) International Publication Date: 27 July 2000 (27.07.00)
(21) International Application Number: PCT/JP99/07144 (22) International Filing Date: 20 December 1999 (20.12.99) (30) Priority Data: 09/234,755 21 January 1999 (21.01.99) US (63) Related by Continuation (CON) or Continuation-in-Part (CIP) to Earlier Application US 09/234,755 (CIP) Filed on 21 January 1999 (21.01.99) (71) Applicant (for all designated States except US): EBARA CORPORATION [JP/JP]; 11-1, Haneda Asahi-cho, Ohta-ku, Tokyo 144-8510 (JP). (72) Inventors; and (75) Inventors/Applicants (for US only): MCCRAY, B., Scott [US/US]; 63415 Saddleback Place, Bend, OR 97701 (US). FRIESEN, T., Dwayne [US/US]; 60779 Currant, Bend, OR 97702 (US). SIDWELL, R., Delores [US/US]; 19072 Pumice Butte Road, Bend, OR 97702 (US). LYON, K., David [US/US]; 20448 Klahani Drive, Bend, OR 97702 (US). SAKASHITA, Daichi [JP/JP]; 7-8-20-101, Shonandai, Fujisawa-shi, Kanagawa 252-0804 (JP).		(74) Agent: HOSOKAWA, Shinya; Yuasa And Hara, Section 206, New Ohtemachi Bldg., 2-1, Ohtemachi 2-cho-me, Chiyoda-ku, Tokyo 100-0004 (JP). (81) Designated States: AU, CA, CN, JP, KR, SG, US, European patent (DE, FR, GB, IT, NL). Published <i>With international search report.</i>
(54) Title: ETHYLENE-VINYL ALCOHOL HOLLOW FIBER MEMBRANES (57) Abstract EVAL microporous hydrophilic hollow fiber membranes are formed from a casting dope that includes low and high molecular weight pore-formers. Post-fabrication treatment includes stretching, hot water soaking and crosslinking.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav	TM	Turkmenistan
BF	Burkina Faso	GR	Greece		Republic of Macedonia	TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's	NZ	New Zealand		
CM	Cameroon		Republic of Korea	PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakhstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

DESCRIPTION

ETHYLENE-VINYL ALCOHOL HOLLOW FIBER MEMBRANES

5 BACKGROUND ART

Hollow fiber membranes have gained acceptance for use in treating many aqueous streams. In some cases, use of hollow fiber membranes is essential for the supply of clean drinking water and for treatment of wastewater. Hollow
10 fiber membranes can also be used to de-water sludges and other streams containing suspended solids. Key to the successful use of such membranes for these purposes is that the membrane be hydrophilic, allowing the membrane to "wet" when in contact with the stream to be treated. For this to
15 occur, the membrane should advantageously be made from a hydrophilic polymer.

One such polymer that has proved suitable for making hydrophilic hollow-fiber membranes is an ethylene-vinyl alcohol (EVAL) copolymer. Such a copolymer is known to be
20 useful in blood dialysis and, because of its hydrophilicity and excellent rejection of high molecular weight substances such as proteins, has many other uses in medical and laboratory applications. Typically, EVAL hollow fiber membranes are cast by forcing a solution of EVAL copolymer
25 through an orifice along with a lumen-forming solution and into a coagulation bath to form membranes having different morphologies and pore structures, depending upon the composition of the casting dope and the process conditions.

See, for example, U.S. Patent Nos. 4,134,837, 4,269,713, 4,317,729 4,362,677, 4,385,094, and Japanese Published Application No. 57-18924. Although a variety of these patents report the use of either a low molecular weight pore-former or a high molecular weight pore-former, there is no recognition of the value of a mixture of both low and high molecular weight pore-formers, and the EVAL membranes prepared according to the processes reported still suffer from a relatively low water flux and limited structural integrity and lifetime when used in applications requiring higher fluid pressures.

DISCLOSURE OF INVENTION

According to the present invention there is provided a process for the fabrication of a strong, durable microporous hydrophilic hollow fiber membrane having high water flux. The process comprises casting the membrane by conventional spinneret technology from a casting dope comprising an EVAL copolymer having a particular composition, followed by a series of post-casting steps.

The casting dope comprises EVAL copolymer in a solvent; a small amount of water; and two pore-formers, one low molecular weight and one high molecular weight. The lumen-forming fluid and the coagulation bath are of conventional composition. After precipitation or coagulation, the hollow fiber membranes are preferably stretched, soaked in hot water, and crosslinked.

BEST MODE FOR CARRYING OUT THE INVENTION

An ideal microporous hydrophilic hollow fiber membrane has three essential characteristics. First, the fiber should have a high water flux. Generally, water
5 fluxes greater than about $2 \text{ m}^3/\text{m}^2 \cdot \text{d} \cdot 0.1 \text{ MPa}$ at 25°C will lead to commercially practical processes. Second, the fiber should have a high wet tensile strength. This will ensure that the fiber has a long lifetime when operating under high pressure differentials, or when the fiber is
10 under stress during operation. Generally, the wet tensile strength of the fiber should be on the order of at least about 180 g/fil . Third, the fiber should have a high wet elongation at break so as to ensure long fiber lifetimes and durability under operating conditions. Generally, the
15 wet elongation at break should be greater than about 40%.

A microporous hydrophilic hollow fiber membrane with such characteristics will be useful for a wide range of applications, including water purification, wastewater treatment and dewatering sludges. The present invention
20 describes a process for the fabrication of such a membrane.

The first step in preparing a microporous hydrophilic hollow fiber membrane according to the present invention is to prepare a spinning solution, comprising a mixture of an EVAL copolymer, a low molecular weight pore-former, a
25 high molecular weight pore-former, water, and a solvent.

Although virtually any EVAL copolymer may be used in the present invention, copolymers with an ethylene content (relative to vinyl alcohol content) of 27 mol% to 48 mol%

are especially suitable.

In making a high-performance membrane, the concentration of EVAL copolymer in the spinning solution should be greater than about 25 wt% based upon the total weight of the spinning solution. If the concentration of copolymer is less than this, the strength of the resulting fiber is too low. Conversely, if the concentration of copolymer is too high, the water flux through the fiber is too low. It has been found that the concentration of EVAL copolymer should be kept in the range of 25 to 40 wt% to obtain practical water fluxes.

The spinning solution preferably contains at least two pore-formers: one with a low molecular weight and one with a high molecular weight. The term "low molecular weight" means ≤ 100 Daltons; and "high molecular weight" means ≥ 1000 Daltons. It has been found that this combination of pore-formers results in a structure suitable for a high-performance membrane. If only a low molecular weight pore-former is used, it has been found that the wall of the resulting fiber contains large voids. These voids reduce the strength of the fiber and are likely to result in defects or damage. In addition, use of only a low molecular weight pore-former leads to an outside surface with little or no porosity, which leads to low water fluxes. Conversely, if only a high molecular weight pore-former is used, it has been found that both the wall and the outside surface of the resulting fiber has low porosity, also leading to low water fluxes. Preferably, the

weight ratio of the low molecular weight pore-former to the high molecular weight pore-former should be greater than about 0.3 but less than about 3. The spinning solution preferably contains the low molecular weight pore-former and the high molecular weight pore-former in an amount of 5 to 15 wt%, respectively, based on the total weight of the spinning solution.

Virtually any low molecular weight pore-former may be used, provided that the compound is not a solvent for the EVAL copolymer and provided it is miscible with the other components of the spinning solution and with the quench baths. Exemplary classes of suitable low molecular weight pore-formers include alcohols, ketones, amines, and esters. It has been found that the most effective low molecular weight pore-formers are mono- and polyhydric alcohols, such as n-propanol, isopropanol (IPA), n-butanol, ethylene glycol (EG), and glycerol.

The high molecular weight pore-former preferably, is soluble in the solvent used to form the spinning solution and miscible in the spinning solution, resulting in solutions that are clear as opposed to cloudy. Exemplary suitable high molecular weight pore-formers include polyols such as polyethylene glycol (PEG), polypropylene glycol (PPG), and polyvinyl alcohol (PVA), polyvinyl pyrrolidone (PVP), and polyethylene oxide (PEO).

The spinning solution preferably also contains a small amount of water, in the order of 0.05 to 1 wt% based on the total weight of the spinning solution. The majority

of this water is preferably introduced to the spinning solution by reason of the addition of the spinning solution's other components since such other components are very hydrophilic and tend to have non-zero concentrations of absorbed water. Since the concentration of water in these other components will depend on the methods used to dry them prior to formulating the spinning solution, it is desirable to add a small amount of water to maintain a total water concentration of between about 0.05 and 1 wt%.

Suitable spinning solution solvents include dimethyl sulfoxide (DMSO), dimethylacetamide (DMAC), dimethylformamide (DMF), and N-methyl pyrrolidone (NMP).

To form the solution, all components should first be thoroughly dried. Then, the components are mixed at elevated temperature, generally 80°C to 100°C, for a suitable length of time, say, 16 to 48 hours. The resulting solution should be clear and have a viscosity ranging from about 30,000 to about 100,000 cp at 65°C. It should be noted that the components of these spinning solutions tend to precipitate when cooled, the temperature at which time the precipitation takes place being dependent upon the specific formulation of the spinning solution. Generally, precipitation takes place when the solutions are cooled below about 50°C. In some cases, the solution will cloud immediately prior to precipitation. It has been found that the solution can be cooled to the point of precipitation, then re-heated to greater than about 65°C so as to re-form

the spinning solution, with no adverse affects on the properties of fibers cast from the reconstituted solution. Preferably, however, the solution should be maintained at a temperature above the precipitation point (around $>50^{\circ}\text{C}$) while it is used, that is, while the solution is extruded to form a spun hollow fiber. In addition, the spinning solution should be filtered and degassed prior to casting hollow fiber membranes.

The membranes are cast by conventional spinneret technology, comprising extruding the spinning solution through the orifice of a needle-in-orifice spinneret. Simultaneously with the extrusion, a coagulating fluid is injected through the needle. Preferably, this coagulating fluid is an aqueous solution such as water alone or a mixture of water and a water-miscible organic fluid, generally characterized by the presence of at least 50 wt% water. Examples of suitable water-miscible organic fluids include low molecular weight alcohols, such as ethanol, IPA, n-propanol, EG and glycerol, and solvents used in the spinning solution, such as those mentioned above (DMSO, DMAC, NMP, and DMF).

From the spinneret, the extruded spinning solution and injected coagulating fluid are drawn into a quench bath consisting of 15 to 35 wt% alcohol in water. Exemplary alcohols include methanol, ethanol, IPA, n-propanol, butanol, EG, and propylene glycol. If the concentration of alcohol is less than about 15 wt%, the fiber quenches too rapidly, leading to a dense outside surface, and low water

fluxes. On the other hand, if the concentration of alcohol is too high, the fiber does not quench rapidly enough, leading to flattened or damaged fibers.

Prior to drawing the extruded spinning solution and
5 injected coagulating fluid into the quench bath, the same may be passed through an atmosphere. This atmosphere may consist of a gas, such as air or nitrogen, and may optionally contain a vapor, such as water vapor, solvent vapors, or other organic vapors. It has been found that
10 passing the extruded spinning solution and injected coagulating fluid through an atmosphere of ambient air for 0.05 to 0.1 second produces suitable fibers.

Another important variable in forming the hollow fiber is the temperature of the quench bath. It has been
15 found that the temperature should be maintained between about 40° C and about 65° C to form high-performance fibers. Generally, the higher the temperature of the quench bath, the larger is the resulting pore size on the outside surface of the membrane.

20 Once the microporous hollow fiber membrane has been formed, it should be rinsed to remove solvents and pore-formers, preferably with water. Generally, the water is maintained at a temperature of greater than about 40° C to ensure proper removal of the residual solvents and
25 pore-formers from the formed hollow fiber membrane. It has also been found that the performance of the fiber, and specifically, its water flux, can be increased by stretching the fiber during this rinsing step. Generally,

the degree of stretching should be such that the ratio of the length of the fiber after stretching to the length of the fiber prior to stretching is between about 1.3 and about 3.0.

5 Once the fiber has been rinsed, it is dried prior to use. In some cases, it is desirable to first rinse the fiber in IPA, then in hexane prior to drying to retain high performance of the fibers.

 The microporous hydrophilic hollow fiber membranes of
10 the present invention are also preferably crosslinked following fabrication. A particularly useful method for crosslinking the fibers involves the use of glutaraldehyde (GA), comprising (1) soaking the fiber in an aqueous GA solution, (2) drying the fiber, and (3) annealing the fiber.
15 In this procedure, the GA solution should be aqueous, and should contain a small amount of an inorganic acid such as HCl as a catalyst. The concentration of GA used in this crosslinking solution should generally be greater than about 0.1 wt% but less than about 5 wt%. The fibers should
20 be soaked in this solution for at least 1 minute, but less than 10 hours. The fiber should then be dried, usually at ambient temperature, to remove excess liquid solution. Drying times ranging from 1 minute to 4 hours have been found to be useful. The annealing step should be conducted
25 at a temperature greater than about 50°C, but less than about 120°C. The annealing step should be conducted for more than about 5 seconds, but less than about 6 hours.

 Another optional post-treatment which has been found

to increase the fiber's water flux is soaking the fiber in hot water (hot water treatment) after the rinsing step. The present inventors has found that membrane performance of the hydrophilic microporous hollow fiber membrane such as flux and elongation at break may be significantly improved by subjecting the fiber to hot water treatment. The hot water treatment is conducted by soaking the prepared hydrophilic microporous hollow fiber membrane in a hot water bath at a temperature of 50° C to 100° C while relaxing tension on the fiber. Relaxation of tension on the fiber in the hot water bath may be carried out by feeding the fiber in a hot water bath using two motorized pulleys, one pulley being used as an inlet pulley by which the fiber membrane is introduced into the bath, and the other pulley being used as an outlet pulley by which the fiber membrane is pulled out from the bath, and maintaining the fiber placed in the bath in a "sagged" state between these two pulleys. It is important in this hot water treatment step for the fiber to be soaked in the hot water bath in fully sagged state, preferably under substantially no tension, such that the fiber may be freely floating in water as if "swimming" in water. If the hot water treatment is carried out while tension is applied to the fiber membrane, flux cannot be improved by this treatment.

The hot water treatment may be carried out for a term of 1 second to 1 hour. This treatment will result in better effect when the fiber is sufficiently swelled with water prior to the treatment. The hot water treatment may improve

flux and elongation at break of the fiber membrane without affecting blocking ability or strength of the fiber membrane. The hot water treatment may be conducted just after the rinsing step as mentioned above. Or this hot water
5 treatment may be conducted on a fiber membrane after the fiber membrane is rinsed and dried, and even after being preserved for a long period of time, to improve mechanical properties of the fiber membrane. However, in order to accomplish significant improvement of membrane
10 performance, it is necessary to conduct the hot water treatment before the crosslinking step as mentioned above.

The thus heat treated hydrophilic microporous hollow fiber membrane may be taken up onto a drum. It is preferred that the fiber membrane is taken up onto a drum placed in
15 warm water at a temperature of 30° C to 70° C, and maintained therein for around one night. Thereafter, the fiber membrane taken up onto the drum in water may be preserved in cold water at a temperature of 10-20° C. By conducting such a post-treatment step, improved membrane performance
20 may be stabilized. When the crosslinking step is carried out after the hot water treatment, the fiber membrane preserved in cold water may be directly fed to the crosslinking step.

25

EXAMPLE 1

A microporous hydrophilic hollow-fiber membrane according to the present invention was fabricated using the following steps.

1. Preparation of the Spinning Solution. A

spinning solution was prepared by dissolving 30 wt% EVAL
copolymer containing 44 mol% ethylene (EVAL Co. of America,
Lisle, Illinois), 8.5 wt% PEG having a molecular weight of
5 3350 Daltons, 8.5 wt% EG, and 0.13 wt% water in DMSO by
mixing said components at 80° C for 16 hours. The resulting
homogeneous solution had a viscosity of 50,000 cp at 65° C.
This solution was maintained at 65° C prior to spinning.

2. Spinning the Hollow Fiber. The so-formed spinning
10 solution was extruded through the orifice of a needle-
in-orifice spinneret. A lumen-forming solution of water
was injected simultaneously through the needle. The tip of
the needle was maintained about 1 cm above the quench bath.

3. Quenching and Rinsing. The spun fiber was formed
15 into a hollow fiber membrane by drawing it into a quench
bath whereupon it precipitated. The bath comprised 25 wt%
IPA in water maintained at 50° C. The residence time in the
quench bath was approximately 20 seconds. The fiber was
then rinsed for about 15 minutes in a godet filled with
20 water at 50° C, then stretched by a factor of 2.4, i.e., the
take-up speed was 2.4 times faster than the godet speed,
then taken up onto a drum and further rinsed in hot water
maintained at 40° -50° C. The fibers were then removed from
the drum and rinsed overnight in hot water maintained at
25 45° -50° C.

4. Drying. The fibers were removed from the overnight
rinse and soaked in 100% IPA for 10 minutes and then in 100%
hexane for an additional 10 minutes prior to drying at

ambient temperature in a dry air stream.

The dried hollow-fiber membranes were examined under a scanning electron microscope (SEM). The inside diameter of the fibers was found to be 330 μm , while the outside diameter was 875 μm . The wall structure was seen to be highly porous, while the outside surface also exhibited a high porosity--both characteristics of high-performance membranes.

Samples of these fibers were then incorporated into a small test module and the outside of the fibers was pressurized to 0.3 MPa at ambient temperature, with filtered, deionized water. The water flux through the fibers was found to be outstanding at 10 $\text{m}^3/\text{m}^2 \cdot \text{d} \cdot 0.1 \text{ MPa}$ at 25°C. (The same units were used for measuring the fluxes of all hollow fiber membranes prepared in the Examples.)

Samples of the fibers were also soaked in water at ambient temperature for 1 hour and then tested for tensile strength. The wet tensile strength was found to be close to ideal, at 180 g/fil, while the wet elongation at break was excellent at 73%.

EXAMPLE 2

Post-fabrication crosslinking was performed as follows. Samples of the fibers from Example 1 were soaked in an aqueous solution of 1 wt% GA and 0.4 wt% HCl for 4 hours at room temperature. The fibers were then dried at ambient temperature for 2 hours prior to placing them in an oven for annealing. The temperature of the oven was

increased from ambient temperature to 80° C at a rate of 1° C /min, held at 80° C for 3 hours, and then cooled to ambient temperature over a period of 20 minutes. The properties of the resulting crosslinked fiber were measured following the procedures outlined in Example 1, and the results of the two presented in Table 1.

Table 1

Example No.	Water Flux (m ³ /m ² ·d·0.1 MPa)	Wet Tensile Strength (g/fil)	Wet Elongation Break (%)
1	10	180	73
2*	7.5	420	25

* crosslinked

10

EXAMPLES 3-6

The effects of stretching during rinsing the membranes of the present invention were studied. Microporous hydrophilic hollow fibers were prepared as in Example 1, except that the polymer solution comprised 33 wt% EVAL, 7.5 wt% PEG, 7.5 wt% EG, and 0.13 wt% water in DMSO, and the quench bath consisted of 30 wt% IPA in water. The degree of stretching ("stretch") during the rinse step was varied as shown in Table 2. These results show that if the degree of stretching is low, water flux is low. In addition, too much stretching results in low water fluxes and low elongations at break. Based on these results, the optimum degree of stretching appears to be 2.4.

20

Table 2

Example No.	Stretch	Water Flux ($\text{m}^3/\text{m}^2 \cdot \text{d} \cdot 0.1 \text{ MPa}$)	Wet Tensile Strength (g/fil)	Wet Elongation at Break (%)
3	1.0	0.0	140	230
4	1.8	4.5	120	90
5	2.4	10.0	130	51
6	3.0	1.0	150	42

EXAMPLES 7-10

The effect of the ratio of low molecular weight pore-former to high molecular weight pore-former was studied. Microporous hydrophilic hollow fiber membranes were prepared as in Example 1 except that various ratios of EG to PEG were used in the spinning solution. Samples of the so-cast fibers, together with samples of the fibers from Example 1 were examined by SEM. A summary of the observations from these examinations is presented in Table 3. Based upon the results, it was concluded that when the EG/PEG ratio is too low, the wall structure is nonporous and the outside surface has a low porosity. Conversely, if the EG/PEG ratio is too high, the wall structure has undesirably large voids and the outside surface has no porosity. Accordingly, it was concluded that a preferred range for the low molecular weight to high molecular weight pore-former ratio is from about 0.3 to about 3.0 to obtain a uniformly porous wall structure with a highly porous outside surface.

Table 3

Example No.	EG/PEG Ratio	Wall Structure	Outside Surface Structure
7	No EG	Nonporous	Low porosity
8	0.5	Uniformly porous	Moderate porosity
1	1	Uniformly porous	High porosity
9	3	Uniformly porous	Moderate porosity
10	no PEG	Large voids	No porosity

EXAMPLES 11-28

The effect of varying the crosslinking conditions on the wet tensile strength and wet elongation at break was studied. Microporous hydrophilic hollow fiber membranes were prepared as in Example 2, except that the conditions used for crosslinking the fibers were varied according to the values reported in Table 4, with the results shown in Table 4.

Table 4

Example No.	GA Conc. (Wt%)	Soak Time (min)	Oven Temp. Rate (OC/min)	Oven Temp (OC)	Time in Oven (hr)	Wet Tensile Strength (g/fil)	Wet Elongation at Break (%)
11	1	10	1	80	180	290	33
12	1	30	1	80	180	290	35
13	1	120	1	80	180	340	30
14	1	240	1	80	180	420	25
15	1	5	5	50	5	200	85
16	1	10	5	50	5	220	66
17	1	30	5	50	5	230	72
18	2.5	5	5	50	5	280	52
19	2.5	10	5	50	5	280	43
20	2.5	30	5	50	5	310	42
21	4	5	5	50	5	330	39
22	4	10	5	50	5	310	31
23	4	30	5	50	5	320	36
24	5	1	1	80	180	380	23
25	5	5	1	80	180	430	24
26	5	10	1	80	180	420	24
27	5	30	1	80	180	410	24
28	5	120	1	80	180	400	23

EXAMPLES 29-32

5 The effect of varying the temperature of the quench bath on flux was studied. Microporous hydrophilic hollow fiber membranes were prepared as in Example 1 except that the polymer solution comprised 32.5 wt% EVAL, 7.5 wt% PEG, 7.5 wt% EG, and 0.1 wt% water in DMSO, and the temperature of the quench bath was varied as indicated in Table 5, with

10 the results shown in Table 5.

Table 5

Example No.	Quench Bath Temperature (°C)	Water Flux (m ³ /m ² ·d·0.1 MPa)
29	45	6.2
30	50	7.9
31	53	7.4
32	55	7.0

Examples 33-36

The effects of varying the temperature of the spinning solution was studied. Microporous hydrophilic hollow fiber membranes were prepared as in Examples 29-32 and the temperature of the spinning solution was varied as indicated in Table 6, with the results shown in Table 7.

Table 6

Example No.	Spinning Solution Temperature (°C)	Water Flux (m ³ /m ² ·d·0.1 MPa)
33	57	5.5
34	58	6.5
35	63	9.4
36	66	9.7

Examples 37-38

The following examples show the effect by conducting hot water treatment on the fiber membrane after rinsing or drying and before crosslinking.

A dry hollow fiber membrane obtained in Example 1 was preserved at room temperature for about one month. Thus preserved hollow fiber membrane was subjected to a hot water treatment in a hot water bath. Prior to the hot water treatment, the fiber was soaked in water at ambient temperature (around 20°C) to be swollen until the length

of the fiber is no longer changed. The fiber membrane was then soaked in a hot water bath maintained at 80°C for over one minute. During the hot water treatment, the fiber membrane placed in the hot water bath was maintained to be
5 sagged with no tension being applied thereto as if the fiber membrane was swimming in hot water. The thus treated fiber membrane was picked up from the bath and transferred into a water at ambient temperature (around 20°C) to cool the fiber membrane.

10 Water flux, wet tensile strength and wet elongation at break of the fiber membrane before and after the hot water treatment (HWT) as mentioned above were determined in a similar manner as in Example 1. The results are shown in Table 7 below as Example 37.

15 A hollow fiber membrane was formed and rinsed in a similar manner as in the steps (1)-(3) of Example 1. The thus obtained hollow fiber membrane just after rinsing step was subjected to a hot water treatment in a similar manner as mentioned above. Water flux, wet tensile strength and
20 wet elongation at break of the fiber membrane before and after the hot water treatment were determined in a similar manner as in Example 1. The results are shown in Table 7 as Example 38.

Table 7

Ex No	Clean Water Flux ($\text{m}^3/\text{m}^2 \cdot \text{d} \cdot 0.1 \text{ MPa}$)		Wet Tensile Strength (g/fil)		Wet Elongation at Break (%)	
	before HWT	after HWT	before HWT	after HWT	before HWT	after HWT
37	8.7	21.2	205	190	30	70
38	14.6	24.3	195	184	35	70

The results in Table 7 show that the hot water treatment according to the present invention improves water flux and wet elongation at break of the fiber membrane substantially without affecting tensile strength thereof, and this effect may be obtained either when the hot water treatment is conducted just after rinsing the fiber membrane or after drying and preserving it for a long period of time.

Examples 39-41

These examples show the effect of varying the hot water treatment time. Hydrophilic microporous hollow fiber membrane was prepared as in Example 38 except that the period of time for the fiber membrane to be soaked in the hot water bath (hot water treatment time) was varied. The results are shown in Table 8.

Table 8

Ex No	HWT time (seconds)	Clean Water Flux ($\text{m}^3/\text{m}^2 \cdot \text{d} \cdot 0.1 \text{ MPa}$)	Wet Elongation at Break (%)
39	0	13.1	32
40	5	22.0	86
41	60	21.9	78

The results in Table 8 show that the hot water treatment according to the present invention improves water flux and elongation at break even when the hot water treatment time is as short as 5 seconds.

5

Examples 42-45

Reproducibility of the effect by the hot water treatment was examined. A hollow fiber membrane was formed and rinsed in a similar manner as in the steps (1)-(3) of Example 1. The thus obtained hollow fiber membrane just after rinsing step was subjected to a continuous hot water treatment as explained below. The fiber membrane was passed through the hot water bath maintained at 80°C for around 5 seconds. The hot water bath used in these examples was equipped with two motorized pulleys, one being used as a fiber membrane inlet pulley by which the fiber membrane is introduced into the bath, and the other being used as a fiber membrane outlet pulley by which the fiber membrane is pulled out from the bath. Using these two motorized pulleys, the fiber membrane placed in the hot water bath was maintained to be sagged with no tension being applied between the two pulleys as if the fiber membrane was swimming in hot water. The thus treated fiber membrane was taken up onto a drum placed in warm water at 50°C, and maintained therein over one night, and then dried at ambient temperature in a dry air stream.

The membrane performance after the hot water treatment of the thus obtained hydrophilic microporous

hollow fiber membrane are shown in Table 9.

Table 9

Ex No	Clean Water Flux ($\text{m}^3/\text{m}^2 \cdot \text{d} \cdot 0.1 \text{ Mpa}$)	Wet Tensile Strength (g/fil)	Wet Elongation at Break (%)
42	18.7	190	109
43	20.6	171	79
44	21.2	181	103
45	20.4	207	89

The results in Table 9 show that substantially
 5 equivalent effect are obtained in Examples 42-45, which
 reveals reproducibility of the effect by the hot water
 treatment according to the present invention.

Examples 46-47

10 The effect of the hot water treatment on blocking
 ability of the hollow fiber membrane was examined.
 According to the procedure of Example 38, two hydrophilic
 microporous hollow fiber membranes were prepared and
 subjected to the hot water treatment. Water flux and
 15 rejection of $0.1\mu\text{m}$ particles of the membranes before and
 after HWT were determined. The results are shown in Table
 10.

Table 10

Ex No	Clean Water Flux ($\text{m}^3/\text{m}^2 \cdot \text{d} \cdot 0.1 \text{ MPa}$)		Rejection of 0.1mm particles (%)	
	before HWT	after HWT	before HWT	after HWT
46	6.8	15.0	99	>99
47	7.8	16.4	99	99

20 The above results show that the hot water treatment

according to the present invention will not affect blocking ability of the hollow fiber membrane.

Examples 48-50

5 These examples show the effect of "relaxation" of fiber membrane during the hot water treatment. According to the procedure of Example 38, a hydrophilic microporous hollow fiber membrane was prepared. The fiber membrane was divided into three specimens and each of them was subjected
10 to the hot water treatment. In Example 48, the hot water treatment was carried out at 80°C for 1 minute while no tension was applied to the fiber membrane placed in the hot water bath. In Examples 49 and 50, the hot water treatment was carried out at 80°C for 1.5 minutes (Example 49) or 4
15 minutes (Example 50) while the fiber membrane placed in the hot water bath was strained by means of some pulleys placed in the hot water bath. Water flux and tensile properties before and after HWT were determined. The results are shown in Table 11.

20

Table 11

Ex No	Clean Water Flux (m ³ /m ² ·d·0.1 MPa)		Wet Tensile Strength (g/fil)		Wet Elongation at Break (%)	
	before HWT	after HWT	before HWT	after HWT	before HWT	after HWT
48	10.9	26.8	212	200	31	76
49	10.9	11.6	212	201	31	49
50	10.9	13.2	212	198	31	48

The results of Table 11 show that, if the hot water treatment is carried out while tension is applied to the

fiber membrane, flux and elongation at break of the fiber membrane is not improved.

5 The terms and expressions which have been employed in
the foregoing specification are used therein as terms of
description and not of limitation, and there is no
intention, in the use of such terms and expressions, of
excluding equivalents of the features shown and described
or portions thereof, it being recognized that the scope of
10 the invention is defined and limited only by the claims
which follow.

CLAIMS

1. A process for the fabrication of a microporous hydrophilic hollow fiber membrane from an ethylene-vinyl alcohol copolymer comprising the steps:

- (a) providing a spinning solution comprising 25 to 40 wt% ethylene-vinyl alcohol copolymer, 5 to 15 wt% low molecular weight pore-former, 5 to 15 wt% high molecular weight pore-former, 0.05 to 1 wt% water, and a solvent;
- (b) forming a spun hollow fiber by extruding said spinning solution through an orifice at a temperature above the precipitation point of the solution while simultaneously injecting a coagulating fluid through a needle located in said orifice;
- (c) drawing said spun hollow fiber into a quench bath of 15 to 35 wt% of an alcohol in water at a temperature of 40° to 65° C to form a hydrophilic microporous hollow fiber membrane;
- (d) rinsing said hydrophilic microporous hollow fiber membrane with water; and
- (e) drying said hydrophilic microporous hollow fiber membrane.

2. The process of claim 1 wherein said hollow fiber membrane is stretched during step (d).

3. The process of claim 2 wherein the degree of stretching during step (d) is from about 1.3 to about 3.0.

4. The process of claim 1 including an additional
5 step (f) comprising crosslinking said hollow fiber membrane.

5. The process of claim 4 wherein said crosslinking is conducted by a process comprising the steps:

- 10 (i) soaking said hollow fiber membrane in an aqueous solution of glutaraldehyde;
 (ii) drying said hollow fiber membrane; and
 (iii) annealing said hollow fiber membrane.

15 6. The process of claim 1 wherein the ethylene content of said ethylene-vinyl alcohol copolymer of step (a) is from 27 to 48 mol%.

20 7. The process of claim 1 wherein said low molecular weight pore-former of step (a) is selected from monohydric and polyhydric alcohols.

25 8. The process of claim 1 wherein said high molecular weight pore-former of step (a) is selected from the group consisting of polyethylene glycol, polyethylene oxide, polypropylene glycol, polyvinylpyrrolidone and polyvinyl alcohol.

9. The process of claim 1 wherein said solvent of step (a) is selected from the group consisting of dimethylsulfoxide, dimethylformamide, dimethylacetamide, and N-methylpyrrolidone.

5

10. The process of claim 1 wherein the weight ratio of said low molecular weight pore-former to said high molecular weight pore-former of step (a) is from about 0.3 to about 3.

10

11. The process of claim 1 wherein said spinning solution of step (a) comprises 30 wt% ethylene-vinyl alcohol copolymer, 8.5 wt% ethylene glycol, 8.5 wt% polyethylene glycol, 0.1 wt% water and the solvent is dimethylsulfoxide.

15

12. The process of claim 1 wherein said coagulating fluid of step (b) is selected from the group consisting of water, mixtures of water and alcohols, mixtures of water and solvent, and mixtures of water, alcohols and solvent.

20

13. The process of claim 1 wherein said alcohol in step (c) is selected from the group consisting of methanol, ethanol, n-propanol, isopropanol, butanol, ethylene glycol and propylene glycol.

25

14. The process of claim 13 wherein said quench bath of step (c) comprises 20 to 30 wt% isopropanol in water.

15. The hollow fiber membrane product of the process of claim 1, 2 or 4.

5 16. The product of claim 15 wherein said hollow fiber membrane has a clean water flux greater than $2 \text{ m}^3/\text{m}^2 \cdot \text{d} \cdot 0.1 \text{ MPa}$ at 25°C , a wet tensile strength greater than about 180 g/fil, and a wet elongation at break greater than 40%.

10 17. The process of any one of claims 1-14 further comprising, after the rinsing step (d) and before the drying step (e), the step:

15 (g) subjecting the rinsed hydrophilic microporous hollow fiber membrane to hot water treatment in a hot water bath at a temperature of 50°C to 100°C while relaxing tension on the fiber.

18. A process for improving membrane performance of a microporous hydrophilic hollow fiber membrane comprising the step:

20 (h) subjecting the hydrophilic microporous hollow fiber membrane obtained by the process of any one of claims 1-3 and 6-14 to hot water treatment in a hot water bath at a temperature of 50°C to 100°C while relaxing tension on the fiber

25 19. A process for the fabrication of a microporous hydrophilic hollow fiber membrane comprising crosslinking a hollow fiber membrane obtained by the process of claim

18.

20. The process of claim 19 wherein said crosslinking is conducted by a process comprising the
5 steps:

- (i) soaking said hollow fiber membrane in an aqueous solution of glutaraldehyde;
- (ii) drying said hollow fiber membrane; and
- (iii) annealing said hollow fiber membrane.

10

21. The process of any one of claims 17-20 wherein, in the heat treating step (g) or (h), tension on the fiber is decreased to as close to zero as possible by using two pulleys and allowing the fiber to sag between these
15 pulleys.

22. The process of any one of claims 17-21 wherein, in the heat treating step (g) or (h), the hot water treatment temperature is not less than 80°C.

20

23. The process of any one of claims 17-22 wherein, in the taking up step (h) or (h), the hydrophilic microporous hollow fiber membrane taken up onto the drum is preserved in the water.

25

24. The hollow fiber membrane product of the process of any one of claims 17-23.

INTERNATIONAL SEARCH REPORT

International Application No.

PCT/JP 99/07144

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 B01D69/08 B01D71/38 B01D67/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 B01D

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 747 113 A (KURARAY CO) 11 December 1996 (1996-12-11) page 3, line 30 -page 4, line 17; example 7	1,4,5, 7-11,15
A	FR 2 314 215 A (KURARAY CO) 7 January 1977 (1977-01-07) page 3, line 16 -page 5, line 22 page 11, line 9 - line 3	1,4-6,9, 12,15, 17,23
A	US 3 907 675 A (CHAPURLAT ROBERT ET AL) 23 September 1975 (1975-09-23) column 3, line 7-14 -/-	1,9,13, 15,17,24



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

6 March 2000

Date of mailing of the international search report

14/03/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentkan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 840-2040, Tx. 31 651 spo nl,
Fax (+31-70) 840-8018

Authorized officer

Faria, C

INTERNATIONAL SEARCH REPORT

International Application No

PCT/JP 99/07144

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p>PATENT ABSTRACTS OF JAPAN vol. 004, no. 182 (C-035), 16 December 1980 (1980-12-16) & JP 55 122010 A (KURARAY CO LTD), 19 September 1980 (1980-09-19) abstract</p>	<p>1, 9, 13, 15</p>

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/JP 99/07144

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 0747113	A	11-12-1996	CN 1141233 A	29-01-1997
			JP 9052030 A	25-02-1997
			US 5789081 A	04-08-1998
			US 5976433 A	02-11-1999
FR 2314215	A	07-01-1977	JP 1222318 C	15-08-1984
			JP 52094361 A	08-08-1977
			JP 58056379 B	14-12-1983
			JP 51145474 A	14-12-1976
			CA 1073822 A	18-03-1980
			DE 2625681 A	17-03-1977
			GB 1503270 A	08-03-1978
			US 4134837 A	16-01-1979
US 3907675	A	23-09-1975	FR 2201911 A	03-05-1974
			FR 2233086 A	10-01-1975
			BE 802580 A	21-01-1974
			CA 1027721 A	14-03-1978
			CH 578027 A	30-07-1976
			DE 2337069 A	07-02-1974
			ES 417081 A	01-08-1975
			GB 1420988 A	14-01-1976
			IL 42801 A	30-04-1976
			IT 994997 B	20-10-1975
			JP 49091970 A	03-09-1974
			NL 7309747 A	22-01-1974
			ZA 7304954 A	26-06-1974
JP 55122010	A	19-09-1980	NONE	